



FEYCOLOR®



Corrosion protection

FEYCOLOR GmbH · Maxhüttenstraße 6 · D-93055 Regensburg
Tel. +49(0)941-60497-0 · Fax +49(0)941-60497-30 · info@feycolor.com

www.feycolor.com



Since the use of metals, corrosion has preoccupied mankind. Today's scope of corrosion protection ranges from the protection of a yard gate to famous examples of architecture like the Eiffel Tower or the Golden Gate Bridge. Examples like these prove that the life of constructions at risk of corrosion can be significantly extended by proper corrosion protection treatment.

Economic and ecological aspects are the driving factors in opting for anti-corrosion coatings. Our corrosion inhibiting coatings contribute considerably to a sustainable protection and to a reduction of damage amounting to billions.

For more than 70 years, corrosion protection has been one of the core businesses of FEYCOLOR. Thanks to our many years of experience and our modern research laboratories, we develop innovative and reliable products that are user-oriented for various application

areas. From synthetic resin primers to solvent-free coating systems – we offer a perfect solution for your requirements.

Factory coating or maintenance and renovation of corrosion protection: Our products comply with various national and international standards and factory standards. This is first and foremost the standard DIN EN ISO 12944 as well as the German regulation ZTV-ING part 4 (Additional technical conditions of contract and guidelines for the civil engineering works, part 4: steel constructions).

This brochure serves as a guideline and assistance for the successful implementation of your corrosion protection project. Our experts will be happy to provide you with individual advice.

Substrate preparation

A durable corrosion protection coating depends on the right substrate preparation, the selection of the right coating system and the professional execution of the coating.

The most important information and details can be found in the European standard DIN EN ISO 12944 "corrosion protection of steel constructions by protective coating systems".

A thorough substrate pre-treatment is an important prerequisite for a long-lasting corrosion protection. Irrespective of the degree of contamination, we recommend thorough cleaning of steel surfaces; that is, rolling skin/scale, rust, old coatings and foreign matters must be removed.

Any residual contamination must be firmly adherent and may remain at best only visible as slight stains in the form of spots or stripes.

Depending on the intended use, suitable preparation procedures are dry blasting, wet blasting, flame cleaning, high pressure water jetting, spot blasting, sweep blasting, acid pickling or alkaline cleaning. After cleaning, the substrate must have the minimum degree of cleanliness of Sa 2.5 as defined in DIN EN ISO 12944-4 as well as an average maximum roughness depth of 40-80 µm according to DIN EN ISO 8503-1.

Corrosivity categories	Exterior environment	Interior environment
C1 very low	–	< 60 % relative humidity, heated buildings with neutral atmospheres, e.g. offices, shops, schools, hotels
C2 low	Atmospheres with low level of pollution, dry climate, mostly rural areas	Uninsulated buildings where condensation may occur, e.g. warehouses, gymnasiums
C3 medium	Urban and industrial atmospheres with an average SO ₂ contamination level or moderate coastal climate, low salinity	Rooms with relatively high humidity and some air pollution, production rooms, e.g. laundries, breweries
C4 high	Industrial areas and coastal areas with moderate salinity	Chemical plants, swimming pools, boathouses on seawater
C5 very high	Industrial areas with high humidity and aggressive atmosphere and coastal areas with high salinity	Buildings and areas with almost permanent condensation and with high pollution
CX extreme	Offshore areas with high salinity and industrial areas with extreme humidity and aggressive atmosphere as well as subtropical and tropical atmosphere	Industrial areas with extreme humidity and aggressive atmospheres
Immersion categories	Environments	Examples
Im 1	Fresh water	River structures, hydroelectric power station
Im 2	Sea or brackish water	Steel structures immersed in water without cathodic corrosion protection
Im 3	Soil	Tanks in the soil, steel sheet piles, steel pipes
Im 4	Sea or brackish water	Steel structures immersed in water with cathodic corrosion protection

CORROSION CATEGORY C2



From corrosivity category **C2 (low corrosivity)** onwards, the prescriptions regulating the duration of protection, the binders to be used and the required layer thicknesses begin.

In this area, 1-component coating materials are still frequently used, but the proportion of 2-component coating materials is increasing.

Category C2 covers the following fields of application:

Outdoor area:

- ✓ dry climate
- ✓ rural climate
- ✓ low pollution

Indoor area:

- ✓ unheated buildings
- ✓ temporary condensation
- ✓ storehouses
- ✓ gymnasiums
- ✓ production hall

Coating systems for corrosivity category C2

System number	priming coat			intermediate and/or finishing coat			complete coating		expected duration of protection			
	product group	number of coats	NDFT μm	product group	number of coats	NDFT μm	number of coats	NDFT μm	low	medium	high	very high
Table C2 Corrosivity category C2 for low-alloyed steel, surface pre-treatment: blast cleaning to Sa 2.5, rust grades A, B or C (see ISO 8501-1)												
C2.01	1K AK Primer	1	40 – 80	1K AK Top coat 1K AK MICA	0 – 1	0 – 40	1 – 2	80				
C2.02	1K AK Primer	1	40 – 100	1K AK Top coat 1K AK MICA	0 – 1	0 – 60	1 – 2	100				
C2.03	1K AK Primer	1	60 – 160	1K AK Top coat 1K AK MICA	0 – 1	0 – 100	1 – 2	160				
C2.04	1K AK Primer	1	60 – 80	1K AK Top coat 1K AK MICA	1 – 2	120 – 140	2 – 3	200				
C2.05	2K EP Primer 2K PU Primer	1	60 – 120	2K EP Top coat 2K PU Top coat 2K PU MICA	0 – 1	0 – 60	1 – 2	120				
C2.06	2K EP Primer 2K PU Primer	1	80 – 100	2K EP Top coat 2K PU Top coat 2K PU MICA	1	80 – 100	2	180				
C2.07	2K EP Zinc rich 1K ESI Zinc rich	1	60				1	60				
C2.08	2K EP Zinc rich 1K ESI Zinc rich	1	60 – 80	2K EP Top coat 2K PU Top coat 2K PU MICA	1	80 – 100	2	160				
Table G3 Corrosivity category C2 for hot-dip galvanized steel												
G2.01	2K EP Top coat 2K PU Top coat 2K PU MICA	1	80				1	80				
G2.03	2K EP Primer 2K PU Primer	1	80 – 120	2K EP Top coat 2K PU Top coat 2K PU MICA	0 – 1	0 – 40	1 – 2	120				

NDFT = nominal dry film thickness

CORROSION PROTECTION CATEGORY C3



The advanced corrosion protection begins with corrosion protection category **C3 (moderate corrosivity)**. In this case, 2-component products are mainly used, which meet the increasing requirements.

Category C3 covers the following fields of application:

Outdoor area:

- ✓ urban and industrial areas with moderate pollution by sulphur oxide
- ✓ coastal areas with low salinity

Indoor area:

- ✓ production rooms with high humidity and some air pollution like e.g laundries, breweries
- ✓ industrial facilities
- ✓ dwelling house
- ✓ roofs

Coating systems for corrosivity category C3

System number	priming coat			intermediate and/or finishing coat			complete coating		expected duration of protection			
	product group	number of coats	NDFT μm	product group	number of coats	NDFT μm	number of coats	NDFT μm	low	medium	high	very high
Table C3 Corrosivity category C3 for low-alloyed steel, surface pre-treatment: blast cleaning to Sa 2.5, rust grades A, B or C (see ISO 8501-1)												
C3.01	1K AK Primer	1	80 – 100	1K AK Top coat 1K AK MICA	0 – 1	0 – 20	1 – 2	100				
C3.02	1K AK Primer	1	60 – 160	1K AK Top coat 1K AK MICA	0 – 1	0 – 100	1 – 2	160				
C3.03	1K AK Primer	1	60 – 80	1K AK Top coat 1K AK MICA	1 – 2	120 – 140	2 – 3	200				
C3.04	1K AK Primer	1	60 – 80	1K AK Top coat 1K AK MICA	1 – 3	180 – 200	2 – 4	260				
C3.05	2K EP Primer 2K PU Primer	1	80 – 120	2K EP Top coat 2K PU Top coat 2K PU MICA	0 – 1	0 – 40	1 – 2	120				
C3.06	2K EP Primer 2K PU Primer	1	80 – 160	2K EP Top coat 2K PU Top coat 2K PU MICA	1	20 – 80	2	180				
C3.07	2K EP Primer 2K PU Primer	1	80 – 160	2K EP Top coat 2K PU Top coat 2K PU MICA	2	80 – 160	2 – 3	240				
C3.08	2K EP Zinc rich 1K ESI Zinc rich	1	60				1	60				
C3.09	2K EP Zinc rich 1K ESI Zinc rich	1	60 – 80	2K EP Top coat 2K PU Top coat 2K PU MICA	1	80 – 100	2	160				
C3.10	2K EP Zinc rich 1K ESI Zinc rich	1	60 – 80	2K EP Top coat 2K PU Top coat 2K PU MICA	1 – 2	120 – 140	2 – 3	200				
Table G3 Corrosivity category C3 for hot-dip galvanized steel												
G3.01	2K EP Top coat 2K PU Top coat 2K PU MICA	1	80				1	80				
G3.02	2K EP Primer 2K PU Primer	1	80 – 120	2K EP Top coat 2K PU Top coat 2K PU MICA	0 – 1	0 – 40	1 – 2	120				
G3.04	2K EP Primer 2K PU Primer	1	80	2K EP Top coat 2K PU Top coat 2K PU MICA	1	80	2	160				

NDFT = nominal dry film thickness

CORROSIVITY CATEGORY C4



The corrosivity category **C4 (high corrosivity)** requires high performance from the paint components used. For these areas, basically 3-layer coating structures are applied. In case of 2-layer systems, only high-build coating structures are used.

Category C4 covers the following fields of application:

Outdoor area:

- ✓ industrial areas with permanent exposure to industrial atmosphere and coastal areas with moderate salinity
- ✓ industrial areas, industrial facilities and dwelling houses in coastal areas with moderate salinity, like e.g. chemical plants, bridges

Indoor area:

- ✓ chemical plants
- ✓ swimming pools
- ✓ coastal shipyards
- ✓ boat harbours

Coating systems for corrosivity category C4

System number	priming coat			intermediate and/or finishing coat			complete coating		expected duration of protection			
	product group	number of coats	NDFT μm	product group	number of coats	NDFT μm	number of coats	NDFT μm	low	medium	high	very high
Table C4 Corrosivity category C4 for low-alloyed steel, surface pre-treatment: blast cleaning to Sa 2.5, rust grades A, B or C (see ISO 8501-1)												
C4.01	1K AK Primer	1	60 – 160	1K AK Top coat 1K AK MICA	0 – 1	0 – 100	1 – 2	160				
C4.02	1K AK Primer	1	60 – 80	1K AK Top coat 1K AK MICA	1 – 2	120 – 140	2 – 3	200				
C4.03	1K AK Primer	1	60 – 80	1K AK Top coat 1K AK MICA	1 – 3	180 – 200	2 – 4	260				
C4.04	2K EP Primer 2K PU Primer	1	80 – 120	2K EP Top coat / 2K PU Top coat 2K PU MICA	0 – 1	0 – 40	1 – 2	120				
C4.05	2K EP Primer 2K PU Primer	1	80 – 160	2K EP Top coat / 2K PU Top coat 2K PU MICA	1	20 – 80	2	180				
C4.06	2K EP Primer 2K PU Primer	1	80 – 160	2K EP Top coat / 2K PU Top coat 2K PU MICA	1 – 2	80 – 160	2 – 3	240				
C4.07	2K EP Primer 2K PU Primer	1	80 – 120	2K EP Top coat / 2K PU Top coat 2K PU MICA	1 – 3	180 – 220	2 – 4	300				
C4.08	2K EP Zinc rich 1K ESI Zinc rich	1	60				1	60				
C4.09	2K EP Zinc rich 1K ESI Zinc rich	1	60 – 80	2K EP Top coat / 2K PU Top coat 2K PU MICA	1	80 – 100	2	160				
C4.10	2K EP Zinc rich 1K ESI Zinc rich	1	60 – 80	2K EP Top coat / 2K PU Top coat 2K PU MICA	1 – 2	120 – 140	2 – 3	200				
C4.11	2K EP Zinc rich 1K ESI Zinc rich	1	60 – 80	2K EP Top coat / 2K PU Top coat 2K PU MICA	2 – 3	180 – 200	3 – 4	260				
Table G4 Corrosivity category C4 for hot-dip galvanized steel												
G4.01	2K EP Top coat / 2K PU Top coat 2K PU MICA	1	80				1	80				
G4.02	2K EP Primer 2K PU Primer	1	80 – 120	2K EP Top coat / 2K PU Top coat 2K PU MICA	0 – 1	0 – 40	1 – 2	120				
G4.04	2K EP Primer 2K PU Primer	1	80	2K EP Top coat / 2K PU Top coat 2K PU MICA	1	80	2	160				
G4.06	2K EP Primer 2K PU Primer	1	80	2K EP Top coat / 2K PU Top coat 2K PU MICA	1 – 2	120	2 – 3	200				

NDFT = nominal dry film thickness



The corrosivity category **C5 (very high corrosivity)** stands for a very demanding corrosion protection at the highest level. 2-component paint systems are used almost exclusively to achieve high coating thicknesses.

Category C5 covers the following fields of application:

Outdoor area:

- ✓ industrial areas with high air humidity and aggressive atmosphere and coastal areas with high salinity, e.g. crane installation in harbours

Indoor area:

- ✓ buildings and areas with almost permanent condensation and with high pollution

Coating systems for corrosivity category C5

System number	priming coat			intermediate and/or finishing coat			complete coating		expected duration of protection			
	product group	number of coats	NDFT μm	product group	number of coats	NDFT μm	number of coats	NDFT μm	low	medium	high	very high
Table C5 Corrosivity category C5 for low-alloyed steel, surface pre-treatment: blast cleaning to Sa 2.5, rust grades A, B or C (see ISO 8501-1)												
C5.01	2K EP Primer 2K PU Primer	1	60 – 160	2K EP Top coat 2K PU Top coat 2K PU MICA	1	20 – 120	2	180				
C5.02	2K EP Primer 2K PU Primer	1	80 – 160	2K EP Top coat 2K PU Top coat 2K PU MICA	1 – 2	80 – 180	2 – 3	240				
C5.03	2K EP Primer 2K PU Primer	1	80 – 240	2K EP Top coat 2K PU Top coat 2K PU MICA	1 – 3	60 – 220	2 – 4	300				
C5.04	2K EP Primer 2K PU Primer	1	80 – 200	2K EP Top coat 2K PU Top coat 2K PU MICA	2 – 3	160 – 280	3 – 4	360				
C5.05	2K EP Zinc rich 1K ESI Zinc rich	1	60 – 80	2K EP Top coat 2K PU Top coat 2K PU MICA	1	80 – 100	2	160				
C5.06	2K EP Zinc rich 1K ESI Zinc rich	1	60 – 80	2K EP Top coat 2K PU Top coat 2K PU MICA	1 – 2	120 – 140	2 – 3	200				
C5.07	2K EP Zinc rich 1K ESI Zinc rich	1	60 – 80	2K EP Top coat 2K PU Top coat 2K PU MICA	2 – 3	180 – 200	3 – 4	260				
C5.08	2K EP Zinc rich 1K ESI Zinc rich	1	60 – 80	2K EP Top coat 2K PU Top coat 2K PU MICA	2 – 3	240 – 260	3 – 4	320				
Table G5 Corrosivity category C5 for hot-dip galvanized steel												
G5.01	2K EP Primer 2K PU Primer	1	80 – 120	2K EP Top coat 2K PU Top coat 2K PU MICA	0 – 1	0 – 40	1 – 2	120				
G5.02	2K EP Primer 2K PU Primer	1	80	2K EP Top coat 2K PU Top coat 2K PU MICA	1	80	2	160				
G5.04	2K EP Primer 2K PU Primer	1	80	2K EP Top coat 2K PU Top coat 2K PU MICA	1 – 2	120	2 – 3	200				
G5.05	2K EP Primer 2K PU Primer	1	80	2K EP Top coat 2K PU Top coat 2K PU MICA	1 – 2	160	2 – 3	240				

NDFT = nominal dry film thickness



In addition to DIN EN ISO 12944 and the ZTV-ING, the Federal there is another guideline from the Bundesanstalt für Straßenwesen (BASt): the TL/TP-ING. In this set of rules Part 4 Section 3 the Technical Delivery Conditions (TL KOR-steel structures) and Technical Test Specifications (TP KOR-steel structures) for coating materials for steel structures in corrosion protection.

In particular, the coating systems for steel structures listed in Blatt 87 form the basis for an initial coating or complete renewal in accordance with TL KOR steel structures with a protection period of at least 25 years.

Approved FEYCOLOR coating systems according to TL KOR-steel structures, Blatt 87

Coating structure	TL- material number	FEYCOLOR System	NDFT*
Steel			
Required surface pre-treatment: blast cleaning to Sa 2 1/2			
Priming coat	687.02	FEYCOPOX 507 2K EP HS Primer, RAL 1002	80 µm
	687.03	OR FEYCOZINK 515 2K EP ZR Primer, grey	
	687.06 (Edge protection)	FEYCOPOX 507 2K EP HS Primer, RAL 8012	(80 µm)
1. Intermediate coat	687.12/13/14	FEYCOPOX 533 2K EP MICA Coating, DB colours	80 µm
	687.17/18	OR FEYCOPUR 643 2K PU EG ZB, DB colours	
2. Intermediate coat	687.12/13/14	FEYCOPOX 533 2K EP MICA Coating, DB colours	80 µm
	687.17/18	OR FEYCOPUR 643 2K PU EG ZB, DB colours	
Finishing coat	687.30 - 74	FEYCOPUR 623 2K PU MICA Coating, DB colours	80 µm
	687.75 - 99	OR FEYCOPUR 626 2K PU DTM Coating, RAL colours	
Total			320 µm (400 µm)
Galvanized steel			
Required surface pre-treatment: sweep blast			
Priming coat	687.12/13/14	FEYCOPOX 533 2K EP MICA Coating DB colours	80 µm
Intermediate coat	687.12/13/14	FEYCOPOX 533 2K EP MICA Coating, DB colours	80 µm
	687.17/18	OR FEYCOPUR 643 2K PU EG ZB, DB colours	
Finishing coat	687.30 - 74	FEYCOPUR 623 2K PU MICA Coating, DB colours	80 µm
	687.75 - 99	OR FEYCOPUR 626 2K PU DTM Coating, RAL colours	
Total			240 µm

NDFT = nominal dry film thickness



The anti-corrosion protective coating for tanks and containers must fulfil additional requirements.

The outer coating must be able to withstand the above-ground or underground influences and stresses, while the lining must be resistant to stresses caused by the goods which are stored in.

With its coatings system compliant to DIN EN ISO 12944 and with its products approved according to Blatt 87 of TL KOR-steel structures, FEYCOLOR offers a wide range of coating systems for these special requirements.

In addition, there are special products for applications in tank and container construction.

Products for tank and container construction

Product	Description	NDFT
Interior Coatings		
Fuel oil tanks – construction and restoration		
FEYCOPUR 437 2K PU Tank Coating	Emission-free and low-odour tank interior coating with excellent adhesion, easy to apply in thick layers. Due to its fast cure (6-12h) the tank can be filled up soon.	300 µm
Mineral oil tanks – construction and restoration		
ALPOTECT 565 2K EP Top Coat	Solvent-free, electrostatically-dissipative EP coating with a contact resistance $< 1 \times 10^8 \Omega$. Suitable for airless or hot spray application.	500 µm
Exterior Coatings		
Underground steel tanks for liquid gas, fuel oil or petrochemical products		
ALPOTECT 568 2K EP Tank Coating	Pore sealing and shock-resistant outer coating for underground tanks made of steel, tested according to DIN 4681-3 by TÜV Süd.	1000 – 1500 µm
Above-ground tanks for liquid gas or LPG filling stations		
FEYCOPUR 649 2K PU HS Coating	For direct to metal application by hot spraying. High-quality coating with a high total solar reflectance, excellent corrosion protection, high weathering and UV resistance.	200 µm

NDFT = nominal dry film thickness



In the atmosphere, in water and in the soil, untreated steel is exposed to corrosion, which causes considerable damage. Steel structures are coated to prevent this damage. To determine the suitable coating materials, it is of great importance to take into account the planned service life and the expected stress level (corrosivity categories).

In order to be able to assess the properties of various products and coating structures better and faster, a number of different test procedures have been laid down in DIN EN ISO 12944-6. The successful performance of these tests, partially supplemented by practical test (e.g. outdoor storage), is the prerequisite for the suitability for the environment in question.

In order to obtain approvals, a recognised institute must carry out the prescribed tests. Upon satisfactory conclusion of the tests, the official test report can be used to provide proof of the anti-corrosion properties or, if necessary, to apply for official approval from the relevant bodies.

Test methods for paint systems for steel EN ISO 12944-6

Corrosivity category according to ISO 12944-2	Level of durability	ISO 2812-2 Water immersion method	ISO 6270-1 Water condensation test	ISO 9227 Effects of salt spray	Periodic aging test
		h	h	h	h
C2	low	–	48	–	–
	medium	–	48	–	–
	high	–	120	–	–
	very high	–	240	480	–
C3	low	–	48	120	–
	medium	–	120	240	–
	high	–	240	480	–
	very high	–	480	720	–
C4	low	–	120	240	–
	medium	–	240	480	–
	high	–	480	720	–
	very high	–	720	1440	1680
C5	low	–	240	480	–
	medium	–	480	720	–
	high	–	720	1440	1680
	very high	–	1200	2160	2688
Im 1	high	3000	1440	–	–
	very high	4000	2160	–	–
Im 2	high	3000	–	1440	–
	very high	4000	–	2160	–
Im 3	high	3000	–	1440	–
	very high	4000	–	2160	–



The dew point (in °C)

The dew point temperature is the temperature at which the air is saturated with water vapour. The lower the temperature, the less water vapour can be absorbed by the air. The water vapour condenses when the temperature decreases to the dew point temperature e.g. on cold steel substrates.

- Air humidity = amount of water vapour in the air
- Absolute air humidity = grams of water per m³ of air
- Maximum air humidity = highest amount of absolute air humidity without precipitation of water in liquid form
- Relative air humidity = depending on the temperature, different ratio between absolute and maximum humidity

On substrates, microscopically dispersed moisture can lead to defective coatings (“coating on water”) due to e.g. dew, mist or condensing air humidity.

The moisture content of the air has furthermore an impact on the drying process of paint and coating materials.

Dew point table

The dew point table indicates the substrate temperatures at which condensation occurs on the surface as a function of air temperature and relative humidity.

Example:

At an air temperature of 22 °C and a relative air humidity of 65 %, condensation will occur on non-absorbent substrates with substrate temperature below 15 °C. As a rule, the substrate temperature during coating and drying should be at least 3 °C above the dew point temperature, i.e. 18 °C in this example.

The detailed dew point table can be found on the penultimate page of this brochure.



Selecting an appropriate coating system

Once the substrate has been prepared accordingly, the appropriate coating system must be selected according to the requirements of DIN EN ISO 12944. First, it is important to specify the environmental conditions of the surface to be coated. For details, see the tables „Corrosivity categories C2 to C5“ on pages 4 – 11. The desired working life of the system must then be determined.

The standard defines the following four level of durability:

low	up to 7 years
medium	7 – 15 years
high	15 – 25 years
very high	more than 25 years

Note: These levels of durability do not correspond to a warranty period, but are a technical consideration that can help the owner set up a maintenance program.

As soon as the category and the durability are determined, the question of an adequate coating system arises. A 3-layer structure consisting of a primer, intermediate and top coat is often applied. The priming coat is of crucial importance as it contains pigments providing passive corrosion protection. The primer is furthermore the base, the adhesion to the substrate as well as the adhesion promoter for the following layers.

The subsequent intermediate coating forms a barrier to penetrating corrosion-promoting substances. This barrier effect is achieved by coat thickness and often also by lamellar pigments.

This layer, which can be adjusted according to the requirements, also levels out minor irregularities on the surface.

The top coat puts the finishing touch to the object. It provides a further barrier to corrosion-promoting substances and an attractive finish. In addition, the top coat offers protection against stresses such as UV-radiation, weathering, aggressive atmosphere as well as chemical agents and/or mechanical stress.

In this brochure, you will find various recommendations for coating structures based on the tables C2 – C5 and G3 – G5 of DIN EN ISO 12944-5. Please note that the following recommendations for coating structures are only options. Individual requirements may also need to be taken into account. Therefore, other products may be more suitable to meet client-specific aspects such as particular mechanical, chemical and weathering resistances or other requirements regarding e.g. gloss or surface feel. If you need expert help and advice in choosing the right product, please contact us.

Application of the coating

The surface must be prepared for coating by following the procedures for surface preparation as described in DIN EN ISO 12944-4. Before applying the coating, please observe the instruction in our technical data sheets. If you have any further questions regarding application, please feel free to contact our application engineers.

Coating material

Product group	Product	Product description	Density approx. kg/l	Solid content approx. %		Mixing ration by weight	NDFT	Theoretical spreading rate approx. g/m ²
				By volume	By weight			
1K ESI Zinc-rich	FEYCOZINK 291 1K ESI ZR Primer	1K Ethylsilikat Zinc Rich Primer grey, matt	3,0	65	90	–	50 – 100	240 – 480
1K KH Primer	FEYALKYD 302 ZN-Phosphate Primer	1K AK Primer for steel, matt	1,5	52	72	–	40 – 100	120 – 300
1K KH Top Coat	FEYCOFIX 340 KH Top Coat	1K AK Top Coat, glossy	1,3	49	66	–	60 – 80	130 – 210
	FEYCOFIX 346 KH Top Coat	1K AK Top Coat, semi gloss	1,4	50	70	–	60 – 80	140 – 230
1K AK DTM	FEYCOFIX 349 DTM Coat HB	1K AK DTM Coating for high build application on steel, semi gloss	1,3	52	69	–	60 – 100	160 – 260
2K EP Primer	FEYCOPOX 505 2K EP Primer	2K EP Primer with Zinc Phosphate, matt	1,5	48	68	5 : 1	60 – 100	190 – 315
	FEYCOPOX 507 2K EP HS Primer	2K EP HS Primer with Zinc Phosphate, matt	1,5	61	79	9 : 1	60 – 100	150 – 250
	FEYCOPOX 510 2K EP	2K EP Primer with Zinc Phosphate, matt	1,4	51	68	5 : 1	60 – 100	175 – 280
	ALPOMASTIC 519 2K EP HS Primer	2K EP HS Primer silver for hand derusted surfaces, semi gloss	1,4	90	94	1 : 1	60 – 100	100 – 160
2K EP Zinc Rich	FEYCOZINK 514 2K EP ZR Primer	2K EP Zinc Rich Primer with high coverage, matt	2,2	67	85	10 : 1	40 – 80	135 – 270
	FEYCOZINK 515 2K EP Zinc Rich	2K EP Zinc Rich Primer grey/reddish grey, matt	2,7	51	83	12 : 1	40 – 80	225 – 450
2K EP MICA	FEYCOPOX 533 2K EP MICA Coating	2K EP MICA Intermediate and Top Coat, matt	1,6	57	74	5 : 1	60 – 120	180 – 360
2K EP Top Coat	FEYCOPOX 535 2K EP HB Coating	2K EP High Build Coating, semi gloss	1,4	59	74	5 : 1	60 – 120	150 – 300
2K PU Grund	FEYCOPUR 610 2K PU	2K PU Metal Primer, matt	1,5	54	73	10 : 1	60 – 100	175 – 280
	FEYCOTECT 616 2K EP-PU	2K EP-PU Primer, matt	1,5	60	78	8 : 1	60 – 100	150 – 255
2K PU MICA	FEYCOPUR 643 2K PU MICA Coating	2K PU MICA Intermediate coat, matt	1,6	63	77	10 : 1	60 – 120	160 – 310
	FEYCOPUR 623 2K PU MICA Coating	2K PU MICA Top Coat, matt	1,6	63	78	10 : 1	60 – 100	165 – 275
2K PU Top Coat	FEYCOPUR 626 2K PU DTM Coating	2K PU Top Coat glossy, semi gloss, satin matt, matt	1,3	55	69	10 : 1	60 – 100	140 – 240
	FEYCOMASTIC 650 2K PU HS GL	2K PU HS Top Coat, glossy	1,4	66	78	8 : 1	80 – 120	170 – 260
	FEYCOMASTIC 652 2K PU HS SG	2K PU HS Top Coat, semi gloss	1,4	67	79	10 : 1	80 – 120	170 – 260

Air temperature in °C	Dew point temperature (rounded) in °C at a relative air humidity of														
	30%	35%	40%	45%	50%	55%	60%	65%	70%	75%	80%	85%	90%	95%	100%
50	28	30	33	35	37	39	40	42	43	44	46	47	48	49	50
45	23	26	28	30	32	34	35	37	38	40	41	42	43	44	45
40	19	22	24	26	28	29	31	32	34	35	36	37	38	39	40
35	15	17	19	21	23	25	26	27	29	30	31	32	33	34	35
30	11	13	15	17	18	20	21	23	24	25	26	27	28	29	30
29	10	12	14	16	18	19	20	22	23	24	25	26	27	28	29
28	9	11	13	15	17	18	20	21	22	23	24	25	26	27	28
27	8	10	12	14	16	17	19	20	21	22	23	24	25	26	27
26	7	9	11	13	15	16	18	19	20	21	22	23	24	25	26
25	6	9	11	12	14	15	17	18	19	20	21	22	23	24	25
24	5	8	10	11	13	14	16	17	18	19	20	21	22	23	24
23	5	7	9	10	12	14	15	16	17	18	19	20	21	22	23
22	4	6	8	10	11	13	14	15	16	17	18	19	20	21	22
21	3	5	7	9	10	12	13	14	15	16	17	18	19	20	21
20	2	4	6	8	9	11	12	13	14	15	16	17	18	19	20
19	1	3	5	7	8	10	11	12	13	15	16	16	17	18	19
18	0	2	4	6	7	9	10	11	13	14	15	15	16	17	18
17	-1	1	3	5	7	8	9	10	12	13	14	15	15	16	17
16	-1	1	2	4	6	7	8	9	11	12	13	14	14	15	16
15	-2	0	2	3	5	6	7	9	10	11	12	13	13	14	15
14	-3	-1	1	2	4	5	6	8	9	10	11	12	12	13	14
13	-4	-2	0	1	3	4	6	7	8	9	10	11	11	12	13
12	-5	-3	0	0	2	3	5	6	7	8	9	10	10	11	12
11	-5	-3	-2	0	1	2	4	5	6	7	8	9	9	10	11
10	-6	-4	-3	-1	0	1	3	4	5	6	7	8	8	9	10
8	-8	-7	-5	-3	-2	0	1	2	3	4	5	6	6	7	8
6	-10	-8	-7	-5	-3	-2	-1	0	1	2	3	4	4	5	6
4	-12	-10	-8	-7	-5	-4	-3	-2	-1	0	1	2	2	3	4
2	-14	-12	-10	-9	-7	-5	-4	-3	-3	-2	-1	0	1	1	2
0	-15	-14	-12	-10	-8	-7	-6	-5	-4	-3	-2	-2	-1	0	0

FEYCOLOR GmbH · Maxhüttenstraße 6 · D-93055 Regensburg
Tel. +49(0)941-60497-0 · Fax +49(0)941-60497-30 · info@feycolor.com

www.feycolor.com